

10/585399

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/001233

International filing date: 13 January 2005 (13.01.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US
Number: 60/536,535
Filing date: 15 January 2004 (15.01.2004)


Date of receipt at the International Bureau: 18 February 2005 (18.02.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

1283429



THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

February 09, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/536,535

FILING DATE: January 15, 2004

RELATED PCT APPLICATION NUMBER: PCT/US05/01233



Certified by

Under Secretary of Commerce
for Intellectual Property
and Director of the United States
Patent and Trademark Office



16898 U.S. PTO

PTO/SB/16 (08-08)

Approved for use through 07/31/2008, OMB 0861-0082

U.S. Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No. _____

U.S. PTO
607536535

INVENTOR(S)					
Given Name (first and middle (if any))		Family Name or Surname		Residence (City and either State or Foreign Country)	
Arnon		HIRSHBERG		Haifa, Israel	
Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (500 characters max)					
INTEGRAL BRITTLINES TEST DEVICE AND METHOD					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input type="checkbox"/> Customer Number: _____					
OR					
<input checked="" type="checkbox"/> Firm or Individual Name c/o Miller - Sieradzki, advocates & patent attorneys					
Address P.O.B. 6146					
Address _____					
City Haifa		State _____		Zip 31061	
Country Israel		Telephone 872-4-8368148		Fax 872-4-8383548	
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification Number of Pages <u>5</u>					
<input checked="" type="checkbox"/> Drawing(s) Number of Sheets <u>2</u>					
<input type="checkbox"/> Application Date Sheet. See 37 CFR 1.76					
<input type="checkbox"/> CD(s), Number _____					
<input type="checkbox"/> Other (specify) _____					
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT					
<input checked="" type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.					
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees.					
<input type="checkbox"/> The Director is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number: _____					
<input checked="" type="checkbox"/> Payment by credit card, Form PTO-2038 is attached.					
FILING FEE Amount (\$) <div style="border: 1px solid black; padding: 5px; width: fit-content; margin: 0 auto;">80.00 USD</div>					
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No.					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____					

[Page 1 of 2]

Respectfully submitted,

SIGNATURE

TYPED or PRINTED NAME Arnon HIRSHBERG

TELEPHONE 872-4-8295582

Date Jan. 8, 2003

REGISTRATION NO. _____

(If appropriate)

Docket Number: 1068/38

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22318-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22318-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

PROVISIONAL APPLICATION COVER SHEET
Additional Page

PTO/SB/16 (08-03)

Approved for use through 07/31/2008. OMB 0581-0032
Trademark Office U.S. DEPARTMENT OF COMMERCE

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

INVENTOR(S)/APPLICANT(S)		
Given Name (first and middle if any)	Family or Surname	Residence (City and either State or Foreign Country)
Matan	NAFTALI	Yoqne'am, Israel
David	ELATA	Haifa, Israel

[Page 2 of 2]

Number 1 of 1

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

Yosef Carmel Miller, advocate
Doron Sieradzki, advocate & patent attorney



יוסף כרמל מילר, עורך דין
דורון שרצקי, עורך דין ופטנטים

Dina Beck-Frimer, advocate
Farha Jubran, advocate

דינה בק-פרימר, עורכת דין
פרחה ג'ובראן, עורכת דין

16698 U.S. PTO
01504

Haifa, 13 January, 2004
Your Ref.:
Our Ref.: 1068/38

U.S. Patent and Trademark Office
2011 South Clark Place
Customer Window, Mail Stop Provisional Patent Application
Crystal Plaza Two, Lobby, Room 1B03
Arlington, Virginia 22202
USA

By Courier - UPS
Contact phone: 703-308-4357

Dear Sirs,

Re: New US Provisional Patent Application
HIRSHBERG et al.
INTEGRAL BRITTLNES TEST DEVICE AND METHOD


Enclosed please find attached a new provisional patent application.

Enclosed documentation includes:

- 1) Specification – 5 pages (2 copies)
- 2) Drawings – 2 sheets (2 copies)
- 3) Provisional Application for Patent Cover Sheet (form PTO/SB/16), duly signed by first named inventor.
- 4) Credit Card Payment Form

Please direct all correspondence in this case to the first named inventor:
Arnon HIRSHBERG
c/o Miller – Sieradzki
P.O.B. 6145
Haifa 31061
Israel

Very truly yours,


Doron Sieradzki

INTEGRAL BRITTLINES TEST DEVICE AND METHOD

The present invention relates to an integral brittleness test device and method for measuring the strength of brittle, deformable microstructures.

Problem Solved by the Invention and its environment:

The present invention relates to the reliability of brittle, deformable structures that are prevalent in Micro-Electro-Mechanical-Systems (MEMS). Main aspects of the present invention address the following considerations: 1) measuring the ultimate strength of the structure in question (i.e., σ_{ult}). 2) conducting said measurement without the necessity of measuring forces or displacements. 3) Conducting said measurement without the necessity of packaging or special handling of the test device (i.e., in microsystems the test can be performed at the "wafer level" without requiring dicing).

Characterization of the strength of deformable elements in MEMS is important for design, and for estimation of reliability. The strength of such elements depends on mechanical properties of the structural material and is strongly affected by the surface texture that is formed during the fabrication process.

Closest Known Related Technology:

Current techniques for characterizing the strength of structural elements in MEMS devices require real-time measurement of displacements and measurement of the applied forces. In some devices (see Fig.1) a "Dog-bone" test structure is axially tensioned up to failure [1]. In these devices failure can occur anywhere along the specimen. In other devices a cantilevered beam is deflected up to failure (see Fig.2), which inevitably occurs at the clamped edge [2]. In both techniques, the maximal applied force is either directly measured, or is deduced from direct measurement of the deflection (and known elastic constants of the tested material). Also, in both techniques the exact location of the failure provides no additional information on the mechanical properties of the structural material.

Novelty

The new test device and method require no measurement of the applied forces or of the resulting deformation. They only require a measurement of the length of the remaining ligament. Due to the simplicity involved in the present invention, the integral test device can be used at the wafer-level (i.e., before dicing) and may be used to calibrate and examine the repeatability of the micromachining process.

Advantages of the Invention:

The present invention has several advantages over the conventional solutions to the problems described above.

- 1) It only requires a measurement of the length of the remaining ligament, In contrast to previous techniques that require dedicated equipment to measure forces or displacements.
- 2) Due to the simplicity of its operation, this device can be used at the wafer-level (i.e., before dicing), In contrast to previous techniques that require delicate handling or expensive packaging process.
- 3) May be used to calibrate and examine the repeatability of the micromachining process.
- 4) May be used to characterize the uniformity in serial processing of wafers.

Full Description of the Invention:

Cantilever beams are deformed up to failure by application of an unmeasured force. The ultimate tensile strength of the beams is directly deduced from the length of the remaining intact ligament of the broken beam.

The maximal tensile stress in a bent beam is equal to the product of the beam curvature, half of the beam width (h in Fig 3a), and the effective elastic modulus. The elastic modulus of the silicon is known and the beam width is measured (for example by optical means). By knowing the exact curvature of the beam at the point of failure, the ultimate tensile strength may be deduced. The cantilever beam in the new test device is wrapped over a wall with prescribed curvature. (For example if the wall is designed such that its curvature is linearly proportional to the circumferential distance from the clamped edge of the beam (see Fig.3). Accordingly, when the beam fails (breaks), the length of the

remaining ligament of the beam is linearly proportional to the ultimate tensile strength.) Note that the prescribed curvature does not necessarily have to be linearly changing curvature, and in fact any prescribed curvature is suitable.

The wrapping of the beam over the curved wall is preferably performed by a micro-manipulator, and the length of the remaining ligament is preferably optically measured (see Fig.3b).

The new device (see Fig.3) may be fabricated from mono-crystalline Silicon with known mechanical properties. However, the beams in this device are preferably micromachined using DRIE - Deep Reactive Ion Etching and their strength depends on the texture of the surface created by this fabrication process.

Many devices are fabricated using this process and usually the process parameters are found by trial and error or by previous experience. This present device and method can shorten the tuning time required to stabilize the process by deducing a direct result for the maximum strength capabilities.

During production this present device and method can be used as a characteristic for the whole wafer, to decide if the wafer continues the process flow or is thrown away (as in "pass / fail" test).

The present invention may be incorporated in the fabrication of wafers by way of including the device in a wafer in order to facilitate in-situ tests.

CLAIMS

1. A device for measuring the tensile strength of a brittle material, the device comprising:

a main body with an integral cantilever beam, the main body having a curved wall, the curved wall designed such that its curvature is known .

2. A method for measuring the tensile strength of a brittle material, the method comprising:

imposing a changeable curvature over a cantilever beam, up to failure (break) of the beam and by measuring the remaining ligament length, deducing the maximum tensile strength.




Figure 1: A "Dog-bone" tension test device. The applied force at failure must be measured. The location of failure provides no additional information.




Figure 2: A cantilever test structure. The applied force must be measured. The failure always occurs at the clamped edge.




Figure 3a: A schematic description of the new test device. The curvature of the cylindrical wall increases linearly with distance from the clamped edge of the beam.




Figure 3b: The length of the remaining ligament after failure is linearly proportional to the ultimate strength of the structural material.